




**KT 55 FA**

### Thermal Paper, Standard Quality

- medium sensitivity
- 10 years durability at correct storage for thermal paper
- produced without using Bisphenol A

Application		POS receipts, fax paper		
Physical Properties		Value	Test Method	
Basis Weight	17 x 22 - 500 sheets	55 ± 5 g/m <sup>2</sup>	ISO 536	
		14.6 ± 1.3 #		
Caliper		60 ± 5 µm 2.36 ± 0.20 mils	ISO 534	
Smoothness (Bekk, front)		≥ 350 s	ISO 5627	
Brightness (front)		≥ 85 %	ISO 2470	
Tensile strength	MD	≥ 40 N / 15 mm	ISO 1924-2	
	CD	≥ 12 N / 15 mm	ISO 1924-2	
Preservation Properties		Optical density before ageing	Optical density after ageing	Conditions
Heat resistance		1.25	≥ 1.20	24h / 50°C
Moisture resistance		1.25	≥ 1.20	24h / 40°C 80% r.h.
Light resistance		1.25	≥ 1.20	24 h / 16,000 lux

### Static Sensitivity



subject to change without notice

### Dynamic Sensitivity

